

WOOD CHARCOAL

STALLION ENERGY'S WOOD CHARCOAL is placed in an oven and cooked. All the volatile gases are driven off and charcoal remains. It burns hot and cleans with virtually no ash. It also burns fast.

Babool Wood is used in making charcoal.



TYPICAL PROPERTIES

| PHYSICAL PROPERTIES | 0-100/80 mm | 0-5 mm | 0-25 mm | 5-25 mm | 25-100 mm |
|----------------------------------|----------------|--------|---------|---------|-----------|
| Total Moisture % max | 8-10 | 8-10 | 8-10 | 8-10 | 5-8 |
| Ash % max (ADB) | 5-8 | 15-18 | 10-15 | 5-8 | 3-5 |
| Volatile Matter % max (ADB) | 16-18 | 16-18 | 16-18 | 16-18 | 12-15 |
| Fixed Carbon (Min) | 75-80 | 60-65 | 65-70 | 75-80 | 78-82 |



